

DESCRIPCIÓN DESCRIPTION / BESCHREIBUNG				CAJAS BOXES / KARTONS / BOÎTES			PALLETES PALLETES / PALETTEN / PALETTES	
FAMILIA Family Famille	FORMATO Format Format	SERIE Serie Série	PZAS. Pcs. Anzahl Pièces	PESO (KG) Weight Gewicht Poids	M2 SQM	CAJAS Boxes Kartons Boîtes	PESO (KG) Weight Gewicht Poids	M2 SQM
RV.PB.	24,3X24,3	MAUI 24	20	18,00	1,18	72	1310	84,96
	24,3X24,3	OMEGA 24	20	18,00	1,18	72	1310	84,96
RV.PB.	24,3X24,3	MAUI 12	20	18,00	1,18	72	1310	84,96
	24,3X24,3	OMEGA 12	20	18,00	1,18	72	1310	84,96
RV.PB.	10,7X53	CLÍO L53	15	12,75	0,85	84	1088	71,40
	10,7X53	DACIA L53	15	12,75	0,85	84	1088	71,40
	10,7X53	MAUI L53	15	12,75	0,85	84	1088	71,40
	10,7X53	OMEGA L53	15	12,75	0,85	84	1088	71,40
RV.PB.	6,5X25	BRUNEI L25	50	9,75	0,82	100	992	82,00
	6,5X25	DACIA L25	50	9,75	0,82	100	992	82,00
	6,5X25	MAUI L25	50	9,75	0,82	100	992	82,00
	6,5X25	TEMPO L25	50	9,75	0,82	100	992	82,00
PV.PC.	15X15	BALI 15	44	19,80	0,99	80	1601	79,20
	15X15	BALTIC 15	44	19,80	0,99	80	1601	79,20
	15X15	COTTAGE 15	44	19,80	0,99	80	1601	79,20
	15X15	PIREO 15	44	19,80	0,99	80	1454	79,20
	15X15	RODAS 15	44	19,80	0,99	80	1454	79,20
	15X15	SAMOA 15	44	19,80	0,99	80	1454	79,20
PV.PC.	22.5X22.5	ALBA 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	ÁPRICA 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	AREZZO 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	BALI 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	BLACK 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	BLANCO 22 VINTAGE	20	20,20	1,01	72	1471	72,72
	22.5X22.5	BOLONIA 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	BOLONIA 22 CENEFA	20	20,20	1,01	72	1471	72,72
	22.5X22.5	BOLONIA 22 ESQUINA	20	20,20	1,01	72	1471	72,72
	22.5X22.5	BOTTICELLI 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	BRESCIA 22 CENEFA	20	20,20	1,01	72	1471	72,72
	22.5X22.5	BRESCIA 22 ESQUINA	20	20,20	1,01	72	1471	72,72
	22.5X22.5	BRINDISI 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	CAGLIARI 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	CIBELES 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	COSENZA 22 BN	20	20,20	1,01	72	1471	72,72
	22.5X22.5	DIONE 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	DORTMUND 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	EGEO 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	FORMENTERA 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	GÉNOVA 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	GOYA 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	GREY 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	KENIA 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	KIOTO 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	LIVORNO 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	LONDON 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	MARQUINA 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	MENORCA 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	MESINA 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	NERJA 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	NERVIÓN 22	20	20,20	1,01	72	1471	72,72

DESCRIPCIÓN DESCRIPTION / BESCHREIBUNG				CAJAS BOXES / KARTONS / BOÎTES			PALLETES PALLETES / PALETTEN / PALETTES	
FAMILIA Family Famille	FORMATO Format Format	SERIE Serie Série	PZAS. Pcs. Anzahl Pièces	PESO (KG) Weight Gewicht Poids	M2 SQM	CAJAS Boxes Kartons Boîtes	PESO (KG) Weight Gewicht Poids	M2 SQM
PV.PC.	22.5X22.5	NOVARA 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	OLITE 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	ORIÓN 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	PALERMO 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	PAVIA 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	PEARL 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	PIREO 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	RÁVENA 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	RODAS 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	SAMOA 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	TITÁN 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	TOKIO 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	URBINO 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	VICENZA 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	WEMBLEY 22	20	20,20	1,01	72	1471	72,72
	22.5X22.5	WHITE 22	20	20,20	1,01	72	1471	72,72
PV.PC.	22,5X25,9	AROSA HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	BALI HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	BALTIC HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	BLACK HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	CAPRICE HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	COMPOSTELA HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	DIONE HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	DORTMUND HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	ESSEN HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	FORMENTERA HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	GINEBRA HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	GREY HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	KENIA HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	LIEJA HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	LONDON HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	LUGANO HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	MALINAS HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	MARQUINA HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	MENORCA HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	NORA HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	ODESA HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	PEARL HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	RÓTERDAM HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	SPLIT HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	TITÁN HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	WEMBLEY HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	WHITE HEX	20	17,50	0,88	60	1067	52,80
	22,5X25,9	YUKON HEX	20	17,50	0,88	60	1067	52,80
PV.PC.	9,9X49,2	BALTIC L50	15	16,05	0,73	84	1365	61,32
	9,9X49,2	BASIC L50	15	16,05	0,73	72	1175	52,56
	9,9X49,2	BÉZIERES L50	15	16,05	0,73	72	1175	52,56
	9,9X49,2	BORGOÑA L50	15	16,05	0,73	72	1175	52,56
	9,9X49,2	BURDEOS L50	15	16,05	0,73	72	1175	52,56
	9,9X49,2	CEILÁN L50	15	16,05	0,73	72	1175	52,56

DESCRIPCIÓN DESCRIPTION / BESCHREIBUNG				CAJAS BOXES / KARTONS / BOÎTES			PALLETES PALLETES / PALETTEN / PALETTES	
FAMILIA Family Familie	FORMATO Format Format	SERIE Serie Série	PZAS. Pcs. Anzahl Pièces	PESO (KG) Weight Gewicht Poids	M2 SQM	CAJAS Boxes Kartons Boîtes	PESO (KG) Weight Gewicht Poids	M2 SQM
PV.PC.	9,9X49,2	CHESTE	15	16,05	0,73	84	1365	61,32
	9,9X49,2	CRACOVIA	15	16,05	0,73	72	1175	52,56
	9,9X49,2	DIONE L50	15	16,05	0,73	84	1365	61,32
	9,9X49,2	DORTMUND L50	15	16,05	0,73	84	1365	61,32
	9,9X49,2	IRATI L50	15	16,05	0,73	72	1175	52,56
	9,9X49,2	KENIA L50	15	16,05	0,73	84	1365	61,32
	9,9X49,2	LONDON L50	15	16,05	0,73	84	1365	61,32
	9,9X49,2	MARQUINA L50	15	16,05	0,73	84	1365	61,32
	9,9X49,2	NIMEGA L50	15	16,05	0,73	72	1175	52,56
	9,9X49,2	TITÁN L50	15	16,05	0,73	84	1365	61,32
	9,9X49,2	WEMBLEY L50	15	16,05	0,73	84	1365	61,32
	19,6X33,8	ANTHE ROMBO	20	17,20	0,89	54	944	48,06
PV.PC.	19,6X33,8	BASILEA ROMBO	20	17,20	0,89	54	944	48,06
	19,6X33,8	BORNEO ROMBO	20	17,20	0,89	54	944	48,06
	19,6X33,8	DAFNE ROMBO	20	17,20	0,89	54	944	48,06
	19,6X33,8	DIONE ROMBO	20	17,20	0,89	54	944	48,06
	19,6X33,8	PANDORA ROMBO	20	17,20	0,89	54	944	48,06
	19,6X33,8	TITÁN ROMBO	20	17,20	0,89	54	944	48,06
PV.PC.	20X120-R	AVIGNON	5	24,95	1,20	45	1142	54,00
	20X120-R	BÉZIERS	4	22,12	0,96	48	1082	46,08
	20X120-R	BORGOÑA	5	24,95	1,20	45	1142	54,00
	20X120-R	BURDEOS	5	24,95	1,20	45	1142	54,00
	20X120-R	RENNES	5	24,95	1,20	45	1142	54,00
PV.PC.	25,8X46,5	FLANDES 46	8	18,20	0,96	72	1325	69,12
	25,8X46,5	MAINE 46	8	18,20	0,96	72	1325	69,12
	25,8X46,5	SAMOA 46	8	18,20	0,96	72	1325	69,12
RV.PC.	9,9X49,2	BASTIA	15	15,29	0,73	84	1301	61,32
RV.GR.	10X50	ITACA	15	16,35	0,75	84	1390	63,00

Bla CARACTERÍSTICAS TÉCNICAS
PORCELÁNICO ESMALTADO
TECHNICAL CHARACTERISTICS GLAZED PORCELAIN TILES
CARACTÉRISTIQUES TECHNIQUES GRÉS CÈRAME ÉMAILLÉ
TECHNISCHE EIGENSCHAFTEN GLASIERTES FEINSTEINZEUG

	ENSAYO / TEST	ENSAYO / TEST	STANDARD	VALOR MEDIO / AVERAGE VALUE
	Ortogonalidad. Rectangularity / Rechwinkligkeit / Angularité.	UNE-EN-ISO 10545-2	± 0,5 % ± 1,5 mm	
	Longitud y anchura. Sides / Seiten / Longueur et largeur.	UNE-EN-ISO 10545-2	± 0,6 % ± 2,0 mm	
	Grosor. Thickness / Dicke / Épaisseur.	UNE-EN-ISO 10545-2	± 5,0 % ± 0,5 mm	
	Curvatura. Curvature / Krümmung / Courbure.	UNE-EN-ISO 10545-2	± 0,5% ± 2,0 mm	
	Resist. a productos domésticos de limpieza. Household chemical resistance / Widerstan- fähigkeit gegenüber Chemischen Househalts Produkten / Résistance aux produits chimiques a l'usage nettoyage.	UNE-EN-ISO 10545-13	Min. Clase GA	Clase GA
	Resistencia a las manchas. Resistance to stainings / Beständigkeit gegen fleckbilder / Résistance aux taches.	UNE-EN-ISO 10545-14	Min. Clase 5	Min. Clase 5
	Resistencia a bajas concentraciones de ácidos y alcalis. Resistance to low concentration of acids and alkalies / Niedrige konzentration con sauren und laugen / Résistance aux faibles concentra- tion d'acides et bases.	UNE-EN-ISO 10545-13	Min. Clase GLA	Clase GLA
	Resistencia a altas concentraciones de ácidos y alcalis. Resistance to high concentration of acids and alkalies / Hohe konzentration con sauren und laugen / Haute résistance a concentration d'acides et bases.	UNE-EN-ISO 10545-13	Min. Clase GHA	Clase GHA

	ENSAYO / TEST	ENSAYO / TEST	STANDARD	VALOR MEDIO / AVERAGE VALUE
	Absorción de agua. Water absorption / Wasseraufnahme / Absortion de l'eau.	UNE-EN-ISO 10545-3	Eb ≤ 0,5 %	Eb ≤ 0,5 %
	Resistencia a la flexión. Bending resistance / Bigefestigkeit / Résistance a la flexion.	UNE-EN-ISO 10545-4	> 35 N/mm²	> 35 N/mm²
	Carga de Rotura. Breaking strength / Bruchfestigkeit / Résistance a la rupture.	UNE-EN-ISO 10545-4	Min. 1300 N	Min. 1300 N
	Resistencia a la abrasión superficial. Resistance to abrasion / Abriebfestigkeit / Résistance a l'abrasion.	UNE-EN-ISO 10545-6	Indicado por el fabricante	Según modelo
	Coefficiente de dilatación térmica. Lineal thermal expansion coefficient / Linearer warme-ausdehnungs koefizient / Coefficient de dilatation thermique lineaire.	UNE-EN-ISO 10545-8	7,0x10+°C	7,0x10+°C
	Resistencia al choque térmico. Resistance to thermal shpck / Temperaturwechselbeständigkeit / Résistance aux écarts de temperature.	UNE-EN-ISO 10545-9		
	Resistencia al hielo. Frost resistance / Frostbeständigkeit / Résistance au gel.	UNE-EN-ISO 10545-12		

BIII CARACTERÍSTICAS TÉCNICAS
TECHNICAL CHARACTERISTICS
CARACTÉRISTIQUES TECHNIQUES
TECHNISCHE EIGENSCHAFTEN

	ENSAYO / TEST	ENSAYO / TEST	STANDARD	VALOR MEDIO / AVERAGE VALUE
	Ortogonalidad. Rectangularity / Rechwinkligkeit / Angularité.	UNE-EN-ISO 10545-2	± 0,5 % ± 1,5 mm	
	Longitud y anchura. Sides / Seiten / Longueur et largeur.	UNE-EN-ISO 10545-2	± 0,5 % ± 2,0 mm	
	Grosor. Thickness / Dicke / Épaisseur.	UNE-EN-ISO 10545-2	± 10,0 % ± 0,5 mm	
	Curvatura. Curvature / Krümmung / Courbure.	UNE-EN-ISO 10545-2	± 0,5% +2,0mm -0,3% -1,5mm	
	Resist. a productos domésticos de limpieza . Household chemical resistance / Widerstan- fähigkeit gegenüber Chemischen Househalts Produkten / Résistance aux produits chimiques a l'usage nettoyage.	UNE-EN-ISO 10545-13	Min. Clase GA	Clase GA
	Resistencia a las manchas. Resistance to stainings / Beständigkeit gegen fleckbilder / Résistance aux taches.	UNE-EN-ISO 10545-14	Min. Clase 5	Min. Clase 5
	Resistencia a bajas concentraciones de ácidos y alcalis. Resistance to low concentration of acids and alkalies / Niedrige konzentration con sauren und laugen / Résistance aux faibles concentra- tion d'acides et bases.	UNE-EN-ISO 10545-13	Min. Clase GLA	Clase GLA
	Resistencia a altas concentraciones de ácidos y alcalis. Resistance to high concentration of acids and alkalies / Hohe konzentration con sauren und laugen / Haute résistance a concentration d'acides et bases.	UNE-EN-ISO 10545-13	Min. Clase GHA	Clase GHA

	ENSAYO / TEST	ENSAYO / TEST	STANDARD	VALOR MEDIO / AVERAGE VALUE
	Absorción de agua. Water absorption / Wasseraufnahme / Absortion de l'eau.	UNE-EN-ISO 10545-3	> 10 %	> 10 %
	Resistencia a la flexión. Bending resistance / Bigefestigkeit / Résistance a la flexion.	UNE-EN-ISO 10545-4	> 12 N/mm²	> 12 N/mm²
	Carga de Rotura. Breaking strength / Bruchfestigkeit / Résistance a la rupture.	UNE-EN-ISO 10545-4	Min. 1000 N	Min. 1000 N
	Coefficiente de dilatación térmica. Lineal thermal expansion coefficient / Linearer warme-ausdehnungs koefizient / Coefficient de dilatation thermique lineaire.	UNE-EN-ISO 10545-8	5,7x10+°C	5,7x10+°C